

BLACK ASPHALT

Asphalt Fence, Roof, & Foundation Coating

DESCRIPTION

Heavy bodied asphalt coating formulated for application on fences, roofs, and foundations.

FEATURES

- Product gives 1 to 3 years weather protection.
- Product initially has high gloss but will flatten to a brownish black color.
- Excellent adhesion to all fence surfaces, can be applied over creosote and CCA salt treated lumber.
- Can be used as a base coat for Premium Asphalt Aluminum. Coat first with Black Asphalt and follow with Premium Asphalt Aluminum at least 4 hours later.
- Clean up with mineral spirits.
- Product viscosity varies with temperature.

RECOMMENDED USES

- Plank fences
- Barns
- Metal roofs
- Run in sheds
- Farm buildings
- Tanks and silos
- Foundations
- Not suitable for flooring or high abrasion surfaces

CHARACTERISTICS

Color	Black with brown cast
Finish	Flat
Flash point	100°F (PMCC)
Viscosity	115 KU @ 77°F
Available Packaging	5-gal pails, 55-gal drums
VOC	Less than 450 grams/liter

SHELF LIFE

2 years in unopened cans. To maximize shelf life, store out of direct sunlight. Product will not be affected if stored below 32°F.

COVERAGE

3 & 4 board fence	12 ft. / gal., both sides
1 board fence	18 ft. / gal., both sides
Flat Surfaces	125 sq. ft. / gal.

Typical fence posts are placed 8 feet apart.

Coverage depends on many factors such as porosity and roughness of the substrate and material losses during application. Using less than recommended material will lead to decreased durability. May require two coats for best results – especially on new wood.

DRYING TIME @ 77°F / RH 50%

Set to touch	24 hours
Re-coat	24 hours
Fully dry	product will continue to gain hardness for several weeks after application.

Drying times vary based on rain, dew, and temperature. Do not paint if rain is expected within 8 hrs.

RECOMMENDED FILM THICKNESS

Wet film – per coat 8.0 to 12.0 mils

APPLICATION

Product should be thoroughly mixed before use. No thinning needed – if necessary, thin with 4 fl. oz. mineral spirits per gal. paint.

Warning: product is combustible and will burn. Use only UL listed heating equipment.

Application temp. above 40°F
Method Brush, roll, or spray

Allow new wood 1 to 3 months to weather to reduce moisture content (less than 15% recommended).

Do not paint the underside of fence planks.

Airless spray:

Rating	1.0 gal / minute minimum
Pressure	1,800-3,000 psi
Filter	none
Tip Size	0.025" to 0.031"

SURFACE PREPARATION

For greatest durability make sure surface is scraped, sanded, or pressure washed thoroughly by removing any peeling or flaking paint before applying. For metal surfaces, ensure surface is clean.