

# FENCECOAT BLACK

## ACRYLIC LACQUER FENCE & BARN PAINT

Direct from the  
Heart of Horse  
Country!

### DESCRIPTION

Lacquer-based paint formulated especially for wood plank fences and barns.

### FEATURES

- Product dries to an extremely tough and durable semi-gloss finish that will not chalk, peel, or rub off.
- Can be applied over virtually any type of marginally prepared surface with excellent results – including asphalt, creosote, and CCA salt treated lumber.
- Can be applied over previously painted or unpainted surfaces.
- Lead free and safe around valuable livestock.
- Not recommended for interior applications.
- Self-priming on all surfaces.
- Will not rub off on horses or humans.
- 4 to 6 years of durability on plank fence, depending on fence condition and surface preparation. Initial coat on new wood will age quicker than recoats.

### RECOMMENDED USES

- Plank fences
- Barn exteriors
- Metal buildings, roofs, and structures
- New and weathered wood
- Concrete
- Silos
- Sheds
- Not suitable for flooring, high traffic areas, interiors, or confined spaces

### CHARACTERISTICS

Color	Black
Finish	Semi-gloss
Flash point	88°F (PMCC)
Viscosity	72 KU
Available Packaging	5-gal pails, 55-gal drums

### SHELF LIFE

2 years in unopened cans. To maximize shelf life, store out of direct sunlight. Product will not be affected if stored below 32°F.

Settling can occur, product must be shaken vigorously before use. For best results, flip pails upside down while shaking.

### COVERAGE

3 & 4 board fence	16 ft. / gal., both sides
1 board fence	26 ft. / gal., both sides
Barns	250 sq. ft. / gal.

Typical fence posts are placed 8 feet apart.

Coverage depends on many factors such as porosity and roughness of the substrate and material losses during application. Using less material than recommended will see a decrease in durability. May require two coats for best results.

### DRYING TIME @ 77°F / RH 50%

Set to touch	4 hours
Re-coat	8 hours
Fully dry	24 hours

Drying times are affected by exposure to sunlight, rain, dew, and temperature. Do not paint if rain is expected within 8 hours.

### RECOMMENDED FILM THICKNESS

Wet film – per coat	6.0 to 10.0 mils
Dry film – per coat	2.0 to 4.0 mils

### APPLICATION

Product should be thoroughly mixed before use. Thinning is not recommended.

Application temp.	Any
Method	Brush, roll, or spray

Allow new wood 1 to 3 months to weather to reduce moisture content. Moisture content of wood should be no more than 15%.

### Do not paint the underside of fence planks.

Airless spray:

Rating	0.5 gal / minute minimum
Pressure	1800-2500psi
Filter	30 to 60 mesh
Tip Size	0.017" to 0.021"

Sprayer must be rated for spraying lacquer. Call us for help determining if your sprayer is capable of spraying this product.

Roller application: use thick nap 7" roller. Clean up with lacquer thinner.

### SURFACE PREPARATION

For greatest durability make sure surface is scraped or pressure washed thoroughly to remove any peeling or flaking paint before applying.